



Evcare VTM

Evcare VTM use Vitamin E wrapped by micro-capsule to finish fabric. It is suitable for cotton, wool, silk, linen, chemical fiber etc. When some external forces affect to the finished fabric, micro-capsules are broken. Then the fabric possesses the function of making skin beautiful and preventing skin from wrinkling.



Nature	Vitamin E
Appearance	Milky white liquid
pH	6.0-7.0
Ionicity	Non-ionic
Solubility	Easily soluble in water

- Characteristics**
1. Make the skin healthy and beautiful
 2. Excellent in humid adsorption and antistatic
 3. Protect the skin from UV damage, reduce the deposition of pigment
 4. Promote blood circulation, improve cardiovascular disease

Application	Padding	Evcare VTM	10.0-30.0g/L
		Temperature	About 25°C
	Dipping	Liquor pick up	Approx. 70-80%
		Dry at 100-120°C	
		Evcare VTM	1.0-3.0%
		Temperature	40-50°C
		Time	20-30min

Storage

If stored properly in its original sealed packaging the shelf life is at least 12 months.
Storage temperature at 0- 40 °C will cause an increase of the color number.
Once the package barrel is opened, it should be used as soon as possible, if not, please seal the left well.

Safety

We know of no ill effects that could have resulted from using this product for the purpose for which it is intended and from processing it in accordance with the current practice. According to the experience we have gained up to now and other information at our disposal, the product does not exert any harmful effects on health, provided that it is used properly, due attention is given to the precautions necessary for handling chemicals, and the information and advice given in our Safety Data Sheet are observed.

Labelling

Please refer to latest Safety Data Sheet for detailed information on product safety.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.